

Technical Sheet

SIMPSON

Strong-Tie

MKSA4

Ring Shank Brick/Wood to Wood Nail

This ring shank nail in stainless steel can withstand rain and aggressive environments. Used where high withdrawal strength is required. A common use is in the construction of jetties, thanks to the nail's corrosion resistance. When laying a brick facade the joins are anchored to an existing cross-wall up to 6 m.



MKSA4

Ring Shank Brick/Wood to Wood Nail

Technical Data

Mitat



Viite	Mitat											
	Tuotenumero	Muu				Mitat ja ominaisarvot[mm]						
		NOBB nr.	DB nr.	Määrä / laatikko	Paino[kg]	d[mm]	L[mm]	d _h [mm]	A _h [mm]	h _t [mm]	l _g [mm]	l _p [mm]
MKSA44.0X100	74229	53292892	1950558	100	0.011	4	100	8.5	56.7	2	50	5
MKSA44.0X125	74230	53292903	1950559	100	0.013	4	125	8.5	56.7	2	50	5
MKSA44.0X145	74231	53292918	1950560	100	0.015	4	145	8.5	56.7	2	50	5
MKSA44.0X175	74232	53292922	1950561	100	0.018	4	175	8.5	56.7	2	50	5
MKSA44.0X200	74233	53292937	1950562	100	0.021	4	200	8.5	56.7	2	50	5

Tuotteen ominaisuudet

Viite	Nail characteristic parameters			
	Tyypillinen vääntölujuus - f _{tor,k} [Nm]			
	Taivutuslujuus - M _{y,k} [Nm][Nm]	Tyypillinen vetoparametri - f _{ax,k,90°} [N/mm²][N/mm²]	Tyypillinen läpivetoparametri - f _{head,k} [N/mm²][N/mm²]	Tyypillinen vetolujuus - f _{tens,k} [kN][kN]
MKSA44.0X100	7825	6.2	-	8.3
MKSA44.0X125	7825	6.2	-	8.3
MKSA44.0X145	7825	6.2	-	8.3
MKSA44.0X175	7825	6.2	-	8.3
MKSA44.0X200	7825	6.2	-	8.3

Refer to relevant ITTR or ETA for more details

Simpson Strong-Tie / Gbo Fastening Systems AB
Bruksvägen 2, 593 75 Gunnebo
tel: 0490-300 00
fax : 0490-233 00

Copyright by Simpson Strong-Tie®

Tämän materiaalin tiedot ovat yksinomaan Simpson Strong-Tie:n © omaisuutta

MKSA4

Ring Shank Brick/Wood to Wood Nail



www.strongtie.fi

SIMPSON

Strong-Tie®